

















MASSTONE	PRODUCT NO.	PIGMENT LOADING	DESCRIPTION	C.I. NO.	LIGHT FASTNESS	ALKALI RESISTANCE
	9B1	20.0%	Black TMPTA	PK 7	8	5
	9W7	55.0%	White TMPTA	PW 6	8	5
	9R110	16.0%	Red TMPTA	PR 52:1	4	4
	9R445	24.0%	Red TMPTA	PR 176	6	5
	9R75	15.0%	(B/S) Red TMPTA	PV 19	8	5
	9R856D	25.0%	(Y/S) Red (PO)NPGDA	PV 19	8	5
	9R89	12.0%	Red TMPTA	PR 149	6	5
	9R1052	15.0%	Magenta DPGDA	PR 122	8	5
	9S4	18.0%	Cyan TMPTA	PB 15:3	8	5
	9S1501	25.0%	Cyan (PO)NPGDA	PB 15:1	8	5
	9S93	10.0%	Violet TMPTA	PV 23	8	5
	9Y750	25.0%	(G/S) Yellow (PO)NPGDA	PY 151	8	3
	9Y97	15.0%	(R/S) Yellow TMPTA	PY 83	5	5
	9G5	20.0%	Green TMPTA	PG 7	7	5
	9N163	36.0%	Burnt Umber (PO)NPGDA	PBr 7:X	8	5
	9N658	40.0%	Burnt Sienna TRPGDA	PBr 7	8	5

